# 3M<sup>TM</sup> Scotchcast<sup>TM</sup> Electrical Insulating Resin 4N

Data Sheet September 2016

## Product Description

3M Scotchcast Electrical Insulating Resin 4N is a two-part, epoxy insulating and encapsulating resin. This resin, mixed in its unique two-part bag, generates its own heat to cure. Its compatibility with solid and synthetic cable insulations and jackets makes Resin 4N an excellent insulator and sealer for cable splicing. Use Scotchcast resin 4N to splice solid dielectric and oil-filled cables up to 8 kV and to jacket high-voltage power cables. It is used in 3M Splice Kit Series 82N and 90-B1N.

3M <sup>™</sup> Scotchcast <sup>™</sup> Electrical Insulating Resin 4N is packaged in the following sizes:					
Size	g	cu. cm.	OZ	cu. in.	
Α	88	78	3.1	4.8	
В	205	181	7.2	11.1	
С	414	366	14.6	22.5	
D	619	548	21.8	33.6	
D-NZ	872	772	30.7	47.3	
Е	288	255	10.1	15.6	

## Agency Approvals & Self Certifications

For RoHS information, please visit www.3M.com/ROHS

#### **Resin Features**

- Excellent multi-purpose moisture sealing resin
- Two-part closed mixing pouch simplifies mixing and pouring
- Bonds to itself and to most modern cable jackets
- · Thermal setting; designed to not melt or run once cured
- Designed to be stable at elevated temperatures
- Generates its own heat to cure
- Tough & Oil resistant

#### **Applications**

- Replace or repair the jacket on both single and multi-core power cables
- Insulate between conductors of multi-core splices operating up to 8kV
- Seal the crotch or sheath when terminating multi-core cables.



### 3M<sup>TM</sup> Scotchcast<sup>TM</sup> Electrical Insulating Resin 4N

#### **Typical Properties**

Physical Property (Test Method)	Typical Value			
Color	US units (metric) Black			
Density (ASTM D792)	0.64 oz/cu in (1,11 g/cu.cm.)			
Hardness (ASTM D2240)	84 Shore D			
Tensile Strength (ASTM D412)	4900 psi (33.8 MPa)			
Elongation (ASTM D412)	4%			
Glass Transition Temperature (ASTM E1356-03)	129°F (54°C)			
Maximum Exotherm (100g) (ASTM D2471-99)	338°F (170°C)			
<b>Gel Time</b> @ 73°F (23°C) (ASTM D2471-99)	16 minutes			
Moisture Absorption @ 73°F (23°C)	2.6% wt. gain in 168 hrs			
Adhesion to Metals (lb/in²) (3M TM456)				
Copper	93.6			
Brass	50.7			
Steel	167.4			
Aluminum	30.9			
Adhesion to Cable Jackets (lb/in²) (3M TM457)				
Vinyl	99.5			
Neoprene	>150			
Nylon				
XLPE	>218			

Electrical Property (Test Method)	Typical Value
Dielectric Strength (ASTM D149)	500 v/mil
Dielectric Constant @ 60Hz (ASTM D150)	
73°F (23°C)	3.1
140°F (60°C)	3.9
194°F (90°C)	6.0
Dissipation Factor @ 60Hz (ASTM D150)	
73°F (23°C)	0.5%
140°F (60°C)	5.1%
194°F (90°C)	>20%

Note: this data is not to be used for specifications. Values listed are typical and should not be considered minimum or maximum.

## Specifications - Product

The material must be supplied in a two-part polyethylene bag with a barrier separating an epoxy and hardener. The barrier must be capable of being broken to permit mixing the two parts without opening the bag.

#### Specifications – Engineering/ Architectural

The material must be 3M Scotchcast Electrical Insulating Resin 4N. It must be packaged in the 3M two-part, closed mixing pouch. The resin must be mixed within the mixing pouch simply by separating the barrier between the two parts of the bag and working the contents back and forth within the bag.

### 3M<sup>TM</sup> Scotchcast<sup>TM</sup> Electrical Insulating Resin 4N

#### **A CAUTION**

If there is any evidence of moisture in the cable, it must be removed and the substrate dried before applying the resin.

### Installation Techniques

Thoroughly clean and dry the surface of the substrate, to which the resin will be bonded. In the case of synthetic cable jackets, the resin must be poured immediately after the surface is prepared to help create a bond.

Remove the closed mixing pouch by tearing the protective envelope.

Premix the darker side of the resin to a smooth consistency, by squeezing, before breaking the barrier. Firmly grasp each flat side of the bag near the center barrier, while pulling the sides of the barrier apart and rolling the sides of thumbs through the barrier. Break the barrier all the way across to the side seals.

Alternately squeeze each end of the bag forcing the resin back and forth. Strip the resin from the corners of the bag. Mix until the color is uniform (30 to 40 squeezes), approximately one to two minutes.

Clip off a corner of the closed mixing pouch and pour into the mold fill spout, maintaining a half-inch head. For the 4D-NZ delivery, break the second seal and pour through the nozzle.

#### **Typical Cure Times:**

Temp Cure Time 70°F (21°C) 1 to 2 hours 50°F (10°C) 4 to 8 hours

**NOTE:** 3M Scotchcast Electrical Insulating Resin 4N is not impaired by freezing; however, it should be warmed to at least 60°F (16°C) before being mixed or poured.

## Handling & Safety Precautions

Read all Health Hazard, Precautionary and First Aid statements found in the Material Safety Data Sheet (MSDS) and/or product label of chemicals prior to handling or use.

## Shelf-Life & Storage

3M Scotchcast Electrical Insulating Resin 4N is stable for a period of three years from date of manufacture when stored at 50-80°F (10-27°C) and below 75% relative humidity.

#### Notes:

- 1. If the guard bag is removed, the shelf life could be reduced to as little as two hours under conditions of high humidity.
- 2. The appearance of fine crystals or hazy appearance on clear side in the liquid resin will not affect product performance.

#### **Availability**

Scotchcast resin 4N is available from your electrical distributor. Check 3M.com/electrical "Where to Buy" for names and locations.

### $3M^{\rm TM} \ Scotchcast^{\rm TM} \ Electrical \ Insulating \ Resin \ 4N$

#### 3M and Scotchcast are trademarks of 3M Company.

Important Notice	All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must	
	evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product, which are not contained in 3M's current publications, or any contrary statements contained on your purchase order, shall have no force or effect unless expressly agreed upon, in writing, by an authorized officer of 3M.	
Warranty; Limited Remedy; Limited Liability	This product will be free from defects in material and manufacture at the time of purchase. 3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. Except where prohibited by law, 3M will not be liable for any direct, indirect, special, incidental or consequential loss or damage arising from this 3M product, regardless of the legal theory asserted.	



Electrical Markets Division 6801 River Place Blvd. Austin, TX 78726-9000 800.245.3573 FAX: 800.245.0329 www.3M.com/electrical

Please recycle © 3M 2016 All rights reserved 78-8141-9404-5 Rev A

### **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Terminals category:

Click to view products by 3M manufacturer:

Other Similar products are found below:

00-054007-01074-6 00-054007-70206-1 00-054007-70210-8 00-054007-70217-7 00-054007-70228-3 00-054007-70256-6 00-054007-70316-7 00-054007-49560-4 00-054007-70209-2 00-054007-70231-3 00-054007-70241-2 00-054007-70242-9 00-054007-70246-7 00-054007-70263-4 00-054007-70288-7 00-054007-70290-0 00-054007-70300-6 00-054007-70304-4 01-2900-1-04412 0190160084 0190350008 600TS-10 605601-1 60617-1-C 61314-6-C 626-0194 63-S M55155/079C01 M55155/099B03 M55155/109H01 M55155/12XH05 M55155/29XJ08 M55155/30-6S M55155/30-9S M55155/30XI09 M6-14RSX 696861-1 696999-1 M86700006 D18-110B-C D18-110B-M 701-1936 701-1955 701-2003 701-2007 701-2013 701-2018 701-2069 701-2077-60 701-2315