## **TECHNICAL DATA SHEET**



## SN100C® LEAD-FREE SOLDER ALLOY

## **FEATURES**

- Liquidus 227°C (441°F)
- Smooth, Bright Solder Joints
- Bridge-Free Soldering
- Low Cost Does Not Contain Silver
- Reduced Copper Erosion from Holes, Pads and Tacks
- Dross Rate Similar to Tin-Lead Alloys
- Omplies with IPC J-STD-006

## **DESCRIPTION**

SN100C is a lead-free silver-free solder alloy developed by Nihon Superior in Japan. SN100C offers user-friendly properties and has been proven in commercial applications since 1999. The inclusion of nickel reduces copper dissolution and produces a bright shiny solder fillet. The addition of germanium reduces dross formation and promotes solder flow. Performance in wave and selective soldering is similar to SAC alloys at considerably lower cost. SN100C is available in bar, solid and cored wire, and solder paste.

## **AVAILABILITY**

SN100C is available in 1.1 kg (2.5 lb) triangular bars, 3 kg AIM Safety Bar and Solid Wire. SN100C is also available in AIM flux cored wire solder and solder paste.

#### TYPICAL ALLOY COMPOSITION

| Typical Alloy Composition |         |          |           |  |
|---------------------------|---------|----------|-----------|--|
| Sn: Balance               | Cu: 0.7 | Ni: 0.05 | Ge: 0.009 |  |

#### TYPICAL MELTING TEMPERATURE

| Typical Melting Temperature |  |
|-----------------------------|--|
| 227°C (441°F) Eutectic      |  |

## TYPICAL SPECIFIC GRAVITY

| Alloy Density                 |
|-------------------------------|
| 7.4 g/cm3 (Archimedes method) |
|                               |



#### **HANDLING & STORAGE**

| Parameter  | Time    | Temperature      |
|------------|---------|------------------|
| Shelf Life | 7 years | Room Temperature |

Solid wire and bar solder products have a shelf life of 7 years under proper storage conditions. For other product categories, refer to those product specific TDS's. Consult the SDS for specific handling procedures.

#### **FLUX COMPATIBILITY**

SN100C bar solder is compatible with all no-clean and water soluble electronic grade fluxes.

## **CLEANING**

Refer to data sheets provided by the flux manufacturer.

#### **SAFETY**

Use with adequate ventilation and proper personal protective equipment. Refer to the accompanying Safety Data Sheet for any specific emergency information. Do not dispose of any hazardous materials in non-approved containers.

Document Rev # NF4 Page 1 of 1

# **X-ON Electronics**

Largest Supplier of Electrical and Electronic Components

Click to view similar products for Solder category:

Click to view products by AIM manufacturer:

Other Similar products are found below:

600YSY 701-2758 707-0425 707-1746 707-1748 707-1811 707-1813 707-1831 707-1840 707-1850 707-1852 13-217-3-01 P10695 SN63WRAP3-.022-1-LB 24-6040-0007 DAC-061 599Z 701-2089 707-0285 707-0366 707-0441-26 707-1774 707-1810 24-6337-9727 601Y 24-9574-7619 24-4060-2437 14-6040-0125 04-0595-0000 V5S35[42G]217 V8B45[60G]138 V5B45[42G]138 V3B45[20G]138 XGS20[20G]158 631960 S2626-O-T 8055 5760140 TRWR-204 1152 EC2002M-1 WPT17 WS6016 760-2028 ART.AGT-030 54068 8S005 4900-18G 648107 811008