



FR-2 COPPER-CLAD LAMINATE

COBRISOL 607 OF - Antimonium free

(Code 606)

DESCRIPTION

NEMA FR-2 UL-V0 paper-phenolic laminate, possessing low odour, with very good thermal behaviour, flame stability, and balanced x,y,z-linear thermal expansion coefficients. Room temperature punching grade, with outstanding quality. The base laminate complies to IEC-249-2-7. Ecological antimonium free grade.

PROPERTIES	TEST CONDITIONS	UNITS	TYPICAL VALUES
Flammability UL-94, 1,5 mm	Sx/x max. Class	A	sec 28/6 V-0
Time to blister at 260°C		A	sec 40
Peel strength, after heat shock 10 sec/260°C		A	N/mm 2,3
Pull-of strength		A	N 150
Water absorption, 1,5 mm	D-24/23		mg 39
Flexural strength, Lengthwise		A	Mpa 180
Crosswise		A	Mpa 160
Surface resistance after damp heat and recovery	C96/40/92		Mohm 5,0E+03
Volume resistivity after damp heat and recovery	C96/40/92		- 5,0E+04
	C96/40/92		- 4,7
Disipation factor after damp heat and recovery 1MHz	C96/40/92		- 0,045
Corrosion at the edges			A/B 1,2
Punchability DIN 53488 at 25°C, Lengthwise/Crosswise		A	0,5/0,5
Bow and twist, 1,5 mm (etched)		B 0,5/150	% 1,4
Punching force, 1,3 mm punch diameter		A	N/mm thick. 450
Stripping force, 1,3 mm punch diameter		A	N/mm thick. 190
Dimensional stability, Lengthwise		E-0,5/150	ppm -800
Crosswise		E-0,5/150	ppm -850
Comparative Tracking Index (CTI)	Laminate side	A	V 200
	Copper side	A	V 225
Odour release at 20 °C (1)		A	o.u./m ² /day <165
x,y,z-linear thermal expansion coefficients (TMA, 50 + 90°C)		A	ppm/°C 14/20/260

Tests according IEC-249-1

(1) Tested on 900 cm² sample, clad one side, after 3 days, according TNO (o.u. = odour unit)

The data is based on typical values of standard production and should be considered as a general information. Our Company reserves the right to future change it is the responsibility of the user to ensure that the product complies with his requirements.

AVAILABILITY

Standard sheet sizes, mm : 2144 x 1160; 1070 x 1160
2540 x 1070; 1270 x 1070
2760 x 1270; 920 x 1270
2050 x 1060; 1025 x 1060

Tolerance: +5/-0 mm
Squariness: 3 mm maximum, as differential
between diagonal measurements

Also available in cut to size panels

Standard size tolerance in cut panels: $\pm 0,3$ m

Material marked by red logo: V0 - VR. undertined
Colour: Light brown






Flexible Cu-Clad

PRODUCT SAFETY DATA SHEET ACCORDING TO EEC/91/155 RULES

ISSUE DATE: 3/0/07
 DATE: 1/0/00
 PRODUCT: VERSION: 2

COBRISOL 607 OF

1. PRODUCT AND COMPANY DATA

PRODUCT NAME (OR TRADE NAME): **COBRISOL 607 OF**

PRODUCT DESCRIPTION:

Cellulose paper-thermosetting phenolic resin laminate, cladded one or both sides with copper foil. Main intended use: base material for printed circuits.

COMPANY ADDRESS:

AISMALIBAR S.A.
 Carreter de Ripollet nº 1
 E-08110 Montcada i Reixac (Barcelona)

EMERGENCY PHONE: (34)-93-5656300 FAX: (34)-93-5656327

2. CHEMICAL COMPOSITION. DATA ON COMPONENTS

Roughly percentage excluding copper:

50%	Cellulose paper
50%	Plasticised phenolic resin

Copper content in standard laminate 1,5 mm, 1 side clad 35 µm, is around 13 %

DANGEROUS COMPONENTS:

DANGER CLASS:

SAFETY PHRASES:

3. HAZARDS IDENTIFICATION

None

4. FIRST AID MEASURES

Not applicable

5. FIRE FIGHTING MEASURES

All the available fire-extinguishing systems could be used. The material is rated as fire resistant. In the event of fire, cautions must be taken with the fumes. Heavy fumes containing phenols, formaldehyde, and hydrogen bromide will be released at temperatures higher than 300°C

6. MEASURES IN CASE OF SPILLAGE

Not applicable

7. HANDLING AND STORAGE

Can be stored in any indoor clima conditions

8. PERSONAL PROTECTION AND LIMITS OF EXPOSURE

INHALATION:

THRESHOLD LIMIT VALUE:

Not applicable

*Work in good ventilated rooms during machining or heating processes
Provide of dust safety suction systems during machining processes
Use personnel dust mask in systemic or prolonged dust exposures*

EYES:

Not applicable

SKIN AND HANDS:

Not applicable

GENERAL HYGIENIC RECOMMENDED RULES

*Keep working clothes clean of dust, by some safety suction device
Wash the hands before eat or drink during working breaks*

9. PHYSICAL AND CHEMICAL PROPERTIES

NATURE: *Solid, polymeric matrix*
COLOR: *Yellowish*
ODOR: *Slightly aromatic*

SPECIFIC GRAVITY:

1,54 kg/m³

(BULK
MASS)

SOLUBILITY IN WATER:

insoluble

IGNITION POINT:

>250 °C

THERMAL DECOMPOSITION FUMES:

See paragraph 5.

10. STABILITY AND REACTIVITY

The product is stable and unreactive in the normal storage and process conditions

11. TOXICOLOGICAL INFORMATION

N/A

12. ECOLOGICAL INFORMATION

*The product is not easily biodegradable
Standard lixiviation tests over material in granular form gives levels lower than 20 mg of free
phenol/liter*

13. DISPOSAL CONSIDERATIONS

WASTE DISPOSAL

*Material could be disposed in underground allowed sites, or incinerated under controlled
conditions. The product is free from dibenzodioxines and dibenzofuranes precursor
components, and antimony compounds. Checking of the local environmental regulations is
strongly recommended*

14. TRANSPORT REQUIREMENTS

None

15. REGULATORY INFORMATION

N/A

10. OTHER INFORMATION

International standards covering the product:

**IEC-249-2-7
NEMA FR-2**

X-ON Electronics

Largest Supplier of Electrical and Electronic Components

Click to view similar products for [Kelan manufacturer](#):

Other Similar products are found below :

[149056](#) [5004](#) [KC-SO-1270/SO-1270](#) [451060](#) [141330](#) [14339](#) [149061](#) [149054](#) [147899](#) [149059](#) [451058](#)