

**Technical Data Sheet**

## Laser/Inkjet Printable Polyolefin Film

This specification is intended to outline the physical and chemical properties of *PANDUIT*'s pressure sensitive laser and inkjet printable polyolefin material and include the following part numbers and printable material identifiers:

Part Number Prefixes		
JL*PO	JLEFPS-*	
LJL*PO-TL	JLEFPD-*	
PLL-*PO-*	CPPLF-S	
EFPL-1	JLCPL-*	

Printable Material Suffixes		
FJJ		

**PRODUCT SPECIFICATIONS:**

Description:	Material is RoHS compliant (European Union directive 2002/95/EC). Material is top coated to provide a laser/inkjet printable surface.
Print Methods:	This material is recommended for laser and inkjet printing.
Adhesive:	Acrylic based, pressure sensitive permanent adhesive.
Standard Colors:	White opaque matte
Thickness:	4.5 +/- 0.6 mils (substrate and adhesive)
Service Temperature Range:	-40°F to 180°F (-40°C to 82°C)
Minimum Application Temperature:	-10°F to 90°F (-23°C to 32°C)
Storage Conditions:	Store at 70°F (21°C) and 50% Relative Humidity.

**PROPERTIES:**

Peel Adhesion to Stainless Steel:  
Shear Adhesion:  
Tensile Strength:  
UV Resistance:  
Elevated Temperature Exposure:

**PERFORMANCE:**

30 oz/in width minimum (PSTC-101, 15 min. dwell)  
2 hours minimum (PSTC-107, Procedure A)  
MD: minimum 7500 PSI (PSTC-131)  
TD: minimum 13000 PSI (PSTC-131)  
\*3000 hours no change observed (ASTM G154)  
After 8 hours at 100°F (37.8°C) there was no deterioration of the substrate

\*3000 hours equates to 5 years of assimilated outdoor UV exposure.

**Technical Data Sheet**

---

**CHEMICAL/SOLVENT RESISTANCE:**

Samples were laser and inkjet printed. These samples were laminated to flat steel panels. The test was conducted at room temperature after 24 hour dwell. The samples were then immersed in the specified reagents for 5 immersions using the following cycle: a 10 minute immersion time followed by a 30 minute recovery time. After the fifth immersion, the samples were rubbed 10 times with a lint free gauze. Visual observations were noted for any adhesive bleed, print smear or loss of legibility.

Chemical Reagent	Visual Observation
Distilled Water	No effect
Mineral Spirits	Slight adhesive bleed
Toluene	Slight adhesive bleed
Isopropyl alcohol	Loss of print legibility
Methanol	Loss of print legibility
Acetone	No effect
Methyl Ethyl Ketone	No effect
1,1,1 Trichloroethane	No effect
Freon TF	No effect
Super Agitene	No effect
Jet A Fuel	No effect
Arco Truslide 68	No effect
SAE 30 Motor Oil	No effect
10% Nitric Acid	No effect

PSTC: Pressure Sensitive Tape Council  
ASTM: American Society for Testing and Materials (U.S.A.)

**LIMITED WARRANTY**

All *PANDUIT* Identification Solution Products (except for Software programs) are warranted to be free from defects in material and workmanship at the time of sale but our obligation under this warranty is limited to replacement of the product proved to be defective within 6 months from the date of sale, or in the case of printers, within 90 days from the date of sale. This warranty is void if the products or printers are modified, altered or misused in any way. Use of *PANDUIT* printers with any product other than the specified *PANDUIT* products for which the printer was designed constitutes misuse. Before using, the user shall determine the suitability of the product for its intended use and user assumes all risk and liability whatsoever in connection therewith. The foregoing may not be altered except by an agreement signed by officers or seller and manufacturer.

NEITHER *PANDUIT* OR SELLER SHALL BE LIABLE FOR ANY OTHER INJURY, LOSS OR DAMAGE, WHETHER DIRECT OR CONSEQUENTIAL, ARISING OUT OF THE USE OF, OR THE INABILITY TO USE THE PRODUCT OR THE PRINTER.

THIS WARRANTY IS MADE IN LIEU OF AND EXCLUDES ALL OTHER WARRANTIES, EXPRESS OR IMPLIED. THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS OF PARTICULAR USE ARE SPECIFICALLY EXCLUDED.

The information contained in this literature is based on our experience to date and is believed to be reliable. It is intended as a guide or use by persons having technical skill at their own discretion and risk. We do not guarantee favorable results or assume any liability in connection with its use. Dimensions contained herein are for reference purposes only. This publication is not to be taken as a license to operate under, or a recommendation to infringe any existing patents. This supersedes and voids all previous literature, etc.

## X-ON Electronics

Largest Supplier of Electrical and Electronic Components

*Click to view similar products for [Wire Labels & Markers](#) category:*

*Click to view products by [Panduit](#) manufacturer:*

Other Similar products are found below :

[89078GBEST](#) [89082GBESR](#) [89082GBEST](#) [PCL025-4](#) [5761-2SF](#) [58400](#) [586R734H02](#) [M1.040.0000.6](#) [CRS-CM5M](#) [CRS-M18M](#) [CS1836-000](#) [CS8626-000](#) [CU6337-000](#) [CU6342-000](#) [CU6343-000](#) [CWD01-0](#) [CWD012-0](#) [CWD012-7](#) [CWD015-3](#) [CWD015-7](#) [CWD02-0](#) [CWD02-3](#) [CWD02-4](#) [CWD02-6](#) [CWD02-8](#) [CWD02-A](#) [CWD02-D](#) [CWD02-H](#) [CWD02-K](#) [CWD02-L](#) [CWD02-M](#) [CWD02-P](#) [CWD02-Q](#) [CWD02-R](#) [CWD02-U](#) [CWD02-W](#) [CWD02-Y](#) [CWD03-+](#) [CWD03-0](#) [CWD03-P](#) [CWD06-0](#) [CWD06-8](#) [CWD06-9](#) [CWD06-L](#) [CWD06-N](#) [CWD09-0](#) [CWD09-5](#) [CWD09-7](#) [6806810001](#) [CZ2857-000](#)